



Technical features:

Strengths:

023 Masking tape 60 °C

Tape structure:

Backing: saturated crepe paper Adhesive: solvent borne rubber / resins adhesive

Characteristics:

Masking tape suitable for any painting in building and construction contexts with temperatures resistance up to 60 °C.

Application fields: building, DIY

painting, indoor, multiple surfaces, no residual

- 60 °C resistance for 1 h
- No residue
- Adaptable to irregular surfaces
- Compatible with solvent and water base paint
- Removal without breaking

Technical	nical information:	Properties	Spec.	Tolerance	Test Method
		Total Weight	90 g/m²	±8%	ISO 536
		Total Thickness	120 µm	± 10 %	AFERA 5006
		MD Tensile strength	> 28 N/cm		AFERA 5004
		MD Elongation at break	> 8 %		AFERA 5004
		Adhesion to steel plate	> 1,8 N/cm		AFERA 5001
		Temperature resistance	60 °C (60 min)		
Ava	ilable colour:	yellow			
Ste	orage details:	 We recommend a storage temperature between 15 and 25 °C The product should not be directly exposed to heat or humidity The product should be conditioned to room temperature before use 			
	Shelf life:	12 months when stored in original carton at 23 °C and max. 50 % relative humidity			
	Remark:	Above figures are for reference and cannot be treated as warranties. Customers are advised to test the material to determine the suitability against intended applications			

IMPORTANT NOTICE TO PURCHASER

All statements technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential, arising out of the use of or the inability to use the product. Before using, users shall determine the suitability of the product for their intended use, and assume all risk and liability whatsoever in connection therewith. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacture.